



# TRESYLENE® 25XX HDPE

## COMPOSITION



High density polyethylene facing

**Low expanded polyethylene foam**

High density polyethylene facing

Contact with product

## CARACTERISTICS

↑ Density	Method N°17	0.25 +/- 10%
↑ Hardness	Shore A	74
↑ Compressibility	Method N°11	66%
↑ Resilience	Method N°11	41%

These values are given according to the best of our current knowledge.

## DIMENSIONS

↑ Thickness	Method N°5	thickness ≤ 2 mm +/-0.2 mm thickness > 2 mm +/-10 %
↑ Diameter	Method N° 6	diam ≤ 50 +/- 0.15 mm - > 50 +/- 0.2 mm
↑ Flatness	Method N° 7	diam ≤ 60 mm thickness > 1.2 mm ≤ 2 % from diameter

## STORAGE AND USE CONDITIONS

These values are given according to the best of our current knowledge.

Liners may be subject to dimensions modifications (particularly flatness or aspect) if recommendation not followed.

↑ Protected from UV	
↑ Temperature	-5°C to 45°C
↑ Relative humidity	30 up to 80%
↑ Shelf life	1 year before wadding - 1 year after wadding

## POSSIBLE PACKING

↑ Loose	↑ Tapes
↑ PE tubes	

## AVAILABLE THICKNESSES

**1.2 mm - 1.5 mm - 1.7 mm - 2 mm – 2.7 mm** For other dimensions, please contact us.

## INFORMATION

These technical information and the uses possibilities are given according to the best of our current knowledge.

We can only favorably prejudge to the trial of the material in the real condition of use.

We remind that the user has to verify: \*compatibility between container and contents\* non modification of the property specifically organoleptic characteristics. Valid except if other specification specified for particular item.

## FOOD APPROVAL

The material is produced with raw materials complying with the European legislation for food contact material. More detailed information is available upon request.

ALOG01-3 – ind a Limited Remedy: If this product is proved to be defective the exclusive remedy available and MGJ's sole obligation shall be, at the customer's option, to either replace the quantity of product proved to be defective or to refund the purchase price. **Limitation of Liability:** MGJ shall not be liable for any direct, indirect, special, incidental or consequential damages based upon breach of warranty, breach of contract, negligence, strict liability or any other legal theory. It is the Customers' responsibility to consider our general conditions of sales.